



- Easy application
- **▼** Matt appearance





# **PRODUCT INFORMATION**

## Consumption

 $2 \text{ kg/m}^2$ 

# Colours

611 colours

#### Storage

1 year in its unopened original packing and stored away from frost and high temperatures.

## **Packaging**

25 kg tub

# Supply

To obtain a consistent colour, it is recommended to only use products with the same batch number on a same facade, as the colour may vary depending on the manufacturing process.

# SPECIFICATIONS AND PERFORMANCES

**Appearance:** coloured grainy paste

Composition: aqueous copolymer dispersion, siloxane resin,

mineral fillers, additives

Density: 1.8

PERFORMANCE MEASURED AT +20°C	
NF T 36-005 standard	Family II Class 2b
NF EN 1062-1 standard	E5 S3 V2 W2 A0



# **FIELD OF USE**

#### Purpose

- Base coat for CRÉALANE "SYSTÈME FIN" on ETICS.
- Decoration of the facades of all types of building.

#### **Authorised bases**

- · Cast concrete.
- Lime-cement render or cement-based render.
- Single-layer render.
- · Wall levelling.
- RHÉAMIX MONO covered with CRÉALANE FOND [RHÉATHERM 600, RHÉATHERM 600 LR systems].

#### **Unauthorised bases**

- Horizontal or pitched outer parts at less than 45° from horizontal
- Outer parts located less than 15 cm above ground level.
- Metallic surfaces.

# **APPLICATION**

#### **Reference documents**

Standard NF P 74-201 / DTU 59.1 of June 2013

#### **Application conditions**

- Application temperature: +5°C to +30°C.
- The base must not be frozen or overheated.
- Do not apply when rain or freezing temperatures are imminent.

## **Precautions for use**

In order to protect your health and the environment, and for the safe use of this product, follow the precautionary advice that is featured on the packing label.

You can find the safety instructions for this product on the Safety Data Sheet (SDS) available on quickfds.com.

#### **Base preparation**

- The base must be clean, sound and free of any non-adhesive parts or areas that could prevent adhesion (for example: release oil, drying products, etc.).
- The base must be level. If necessary, level it with BÉTOMUR or PELLIPLAST wall levelling compound (see data sheets).
- Apply base regulator CRÉALANE FOND (see technical data sheet on pages 86-87).
- Large surface areas:

Make a joint pairing using adhesive paper, which will be removed before the render skin forms.

## **Product preparation**

Mix CRÉALANE T to the bottom of the tub.

## **Application**

WORKABLE TIME AT 20°C	
Drying time	3 to 4 h
Time to final hardening	3 to 4 weeks

- Apply **CRÉALANE T** evenly using a stainless steel or plastic float by pulling it to the thickness of the grain.
- Float in a circular motion to even out and close the surface.
- Clean the tools with water as long as the product is fresh.