

MONOTEMPO

SETTING RETARDANT FOR
SINGLE LAYER RENDERS



RENDERING WORK IN HOT WEATHER

Extends the time before scratching



PRODUCT INFORMATION

Consumption

1 L per 180 kg batch of render (6 x 30 kg bags or 8 x 25 kg bags).

Storage

1 year in its unopened original packing and stored away from frost and high temperatures.

Packaging

25 L container

SPECIFICATIONS AND PERFORMANCES

Appearance: colourless liquid

Density: 1.08

pH: 2 to 3

Increases the time before scraping by 1.5 to 2 hours, depending on the type of render and the application conditions.

FIELD OF USE

Purpose

Delays the setting of single-layer renders in hot weather

Authorised bases

See render technical data sheet

Unauthorised bases

See render technical data sheet

APPLICATION

Application conditions

- See render technical data sheet.
- Application temperature < +35°C.
- Industry practice remains fully applicable.

Precautions for use

In order to protect your health and the environment, and for the safe use of this product, follow the precautionary advice that is featured on the packing label.

You can find the safety instructions for this product on the Safety Data Sheet (SDS) available on quickfds.com.

Base preparation

- See render technical data sheet.
- The use of **MONOTEMPO** does not dispense with the need to moisten the base in hot weather

Product preparation

- Replace **1 L** of mixing water with **1 L** of **MONOTEMPO**.
- This average dosage must be adapted to the chosen render and the application conditions.
- Use the same dose for each batch.

Application

See the render technical data sheet.

The purpose of the information provided on this technical sheet is to inform of the product's current properties. It cannot, under any circumstances, be considered as a guarantee nor as engaging our liability due to varying use and application techniques and materials used. We strongly recommend preliminary testing. When this document was drawn up, all indications were based on current technical development data and our experience. The most recent version is available on www.vicat.fr.